


Developed by Olin Brass in 1964, C194 is a High Performance Alloy used worldwide for a variety of applications including automotive and electrical connectors. Offering a unique combination of good electrical and thermal conductivity with high strength, good solderability and plateability make this alloy an excellent choice to replace standard copper or brass alloys for enhanced performance.

**Chemical Composition**

<b>Copper</b>	<b>97.0%min</b>
<b>Iron</b>	<b>2.1-2.6%</b>
<b>Phosphorus</b>	<b>0.015-0.15%</b>
<b>Zinc</b>	<b>0.05-0.20%</b>
<b>Lead</b>	<b>0.03% max</b>



**Figure 1:** Comparison of Yield Strength and Electrical Conductivity performance of select automotive and electrical connector materials.

**Physical Properties**

	English Units	Metric Units
Density	0.322 lb/in <sup>3</sup> @ 68°F	8.92 g/cm <sup>3</sup>
Thermal Conductivity	150 BTU-ft/ft <sup>2</sup> -hr-°F	260 W/m°K
Electrical Resistivity	17.28 ohm circ mils/ft	2.87 microhm-cm
Electrical Conductivity (annealed)	60% IACS*	0.348 megamho/cm
Modulus of Elasticity	17,500,000 psi	121 kN/mm <sup>2</sup>
Coeff. Of Thermal Expansion	68-572°F (20-300°C)	9.8 PPM/°F
	68-392°F (20-200°C)	9.6 PPM/°F
	68-212°F (20-100°C)	9.3 PPM/°F

\*International Annealed Copper Standard

**Mechanical Properties**

Temper <sup>1</sup>	Tensile Strength		Yield Strength <sup>2</sup>		% Elongation <sup>2</sup>	Typical 90° Bend Formability GW/BW <sup>3</sup>	
	ksi	N/mm <sup>2</sup>	ksi	N/mm <sup>2</sup>			
Annealed	40-63	275-435	38	260	23	-	-
Light Anneal	45-55	310-380	23	160	26	-	-
1/2 Hard	53-63	365-435	45	310	17	0.8	1.0
Hard	60-70	415-485	60	415	7	1.0	1.3
Extra Hard	67-73	460-505	67	460	3	1.5	1.5
Spring Hard	70-76	485-525	70	485	2	1.8	1.8
Extra Spring Hard	73-80	505-550	73	505	2 max		

<sup>1</sup> Mechanical properties subject to change. All tempers listed are made to a Tensile Strength specification unless otherwise noted.

<sup>2</sup> Nominal Values

<sup>3</sup> DATA FOR REFERENCE ONLY. R/T = Bend Radius/Material Thickness <0.016" (0.4mm) thick, 11/16 (17.5mm) wide.

**A J OSTER HEADQUARTERS**

WARWICK, RI  
(401) 736-2600

**A J OSTER**

WOODBURY, CT (Sales)  
(800) 342-7277

**A J OSTER FOILS**

ALLIANCE, OH  
(330) 823-1700

**AJ OSTER WEST**

YORBA LINDA, CA  
(714) 692-1000

**A J OSTER EAST**

WARWICK, RI  
(401) 739-0800

**A J OSTER MIDWEST**

CAROL STREAM, IL  
(630) 260-1040

**AJ OSTER MEXICO**

QUERETARO, MEXICO  
52 (442) 229-4000

**A J OSTER CARIBE**

CAGUAS, PR  
(787) 747-7575